



## TECNOCOAT P-2049 EL - STRETCHABLE PURE POLYUREA MEMBRANE (>600%) FOR WATERPROOFING AND COATING

TECNOCOAT P-2049 EL is a two-component, sprayable, aromatic coating suitable for waterproofing, protection, and sealing. It's made up of two high reactive liquid components, isocyanates and amines, mixed together using our specific spray equipment (TC2049 <http://spray-equipment.tecnopolgroup.com/>) or similar, to form a solid, continuous, watertight and waterproof, seamless, high density and high elastic pure polyurea membrane, with high mechanical qualities, **especially in elements with structural movements.**



## USES

For waterproofing and protection of:

- Metal roofs (zinc,...).
- Construction element on civil works (bridge structures, concrete decks, retaining walls, and foundations)
- In general, structural elements or surfaces that may have high expansion movements due to temperatures
- Flat or sloped asbestos roofs (used with TECNOFOAM, spray polyurethane foam system)
- As a protection for SPF (TECNOFOAM, spray polyurethane foam system)

**NOTE:** call our technical department about the application to other supports or situations

recommended minimum thickness	±1,5 mm
tack-free time	± 13-25 secs
tensile strength	± 13 MPa
elongation at 23°C / -40°C	> 600% / >350%
hardness Shore A	>75%
hardness Shore D	>35
VOC(volatile organic compounds)	0
application method	spray equipment



## COLORS

	White
	Gray
	Black
	Red



## GENERAL FEATURES:

- TECNOCOAT P-2049 EL is a very elastic coating membrane that, once applied, offers waterproofing, great stability, and durability.
- the application and training are done by our spray equipment TC2049 ([spray-equipment.tecnopolgroup.com](http://spray-equipment.tecnopolgroup.com)) or similar
- thanks to its versatility and its drying time of between 13 and 15 seconds TECNOCOAT P-2049 EL adapts to any surface, making it the ideal product for application on uneven surfaces and in areas of any shape, whether curved or squared.
- it saves in seals and any other kind of joins, as the finish is uniform and makes up a single layer, providing a surface with optimum maintenance and cleaning properties.
- recommended consumption is approximately 1,7 kg/sqm (at 1,5 mm dry film thickness). This data could vary depending on the type of application, weather conditions, or substrates' nature.
- it should be applied in dry conditions avoiding the presence of humidity or coming from the surface to be coated or the substrate, whether at the time of application or subsequently (pressure from phreatic water level). In the event there is humidity in the substrate at the time of application, consult the technical specifications of our primers in the TDS.
- the system's properties enable it to bond to any surface, such as cement, concrete, polyurethane, wood, metal, etc. Furthermore, due to its resistance, it can be walked on and it will accept a rough finish to make it non-slip (according to ENV 12633:2003)
- his properties allow it to adhere to any surface such as concrete, ceramic tiles, metals, spray polyurethane foam (Tecnofoam), plywood, asphalt/bituminous sheets. In any case or material, the surface must be consistent, firm, clean, and dry when the products are applied. Recommended applying directly on the concrete deck. Ponding water admitted.
- free from harmful VOC compounds, therefore, it does not hurt the ozone layer (VOC's zero). It's 100% recyclable by mechanical means friendly to the environment; no gas collection for recycling and/or destruction is required; it doesn't emit substance to the environment once installed.
- the system requires solar radiation protection (UV rays) to do not lose its physical and mechanical properties, given that it is an aromatic membrane. The system incorporates a protective polyurethane-colored aliphatic resin, TECNOTOP 2C, for use in the absence of other physical protection elements. You can apply too TECNOTOP S-3000, TECNOTOP 2CP or TECNOTOP 1C.

## PACKAGING

Metal drums of 225 kg each component (B side: amines and A side: isocyanates).

## SHELF LIFE

12 months at temperatures between 5°C to 35°C, provided it is stored in a dry place, keep away from direct sunlight, extreme heat, cold, or moisture. Once the tin has been opened, the product must be used. Once opening drum, B side must be agitated mechanically before inserting the transfer pumps and use.

## APPLICATION METHOD

In general, you should take the following factors:

- repair the surface (fill in depressions, eliminate unevenness, eliminate any old waterproofing, etc.)
- singular points preparation(perimeter, sinks / evacuations, expansion joints or structural)
- remove any silicone-based products
- the surface has to be enough compressive strength of adhesion of the membrane. If it were not so, we will proceed to apply our primers resins to achieve this target



- clean up the surface or substrate, removing any dust, dirt, grease, or efflorescence.

NOTE: in case of doubt of all above, apply before in a restricted area and to check, also carry out some adhesion test

The TECNOCOAT P-2049 EL pure polyurea system can be applied to many different surfaces and the procedure will vary depending on its nature or state. Below we set out some of the applications for the most common surfaces; for other surfaces not described, please contact our technical department.

#### Concrete substrate

- any depressions or voids should be repaired using our epoxy resin PRIMER EP-1010
- the concrete should be completely cured (concrete curing takes 28 days) or, in any case, the maximum level of humidity allowed for the substrate should be verified, depending on the primer used.
- any concrete latencies or release agents should be eliminated and an open-pore surface achieved by grit blasting, milling, or sanding (to achieve a Concrete Surface Preparation index -CSP- 3 to 6 from ICRI Guide 03732, depending on the final use). Recommended CSP 3 or CSP 4.
- on old concretes, some acid-etched is needed to open the pores for primer acceptance
- clean up and eliminate all contaminants from the elements, such as dust or particles from the previous processes.
- apply the primer in the conditions and with the parameters indicated in the technical specifications for these products. In general, the two-component polyurethane PRIMER PU-1050/PRIMER PUc-1050, the epoxies PRIMER EP-1010, PRIMER EP-1020, or PRIMER EPw-1070 should be used, to promote adherence to the concrete surface, reduce the pinhole appearance, and absorption of moisture in the substrate ( please check the primers absorption capacity in the TDS )
- apply the TECNOCOAT P-2049 EL pure polyurea coating.
- application of the aliphatic resin TECNOTOP S-3000/2C/2CP/1C in consumption and desired thicknesses in the case of no protection against UV rays.

#### Metal substrate:

- metal surfaces should be prepared using sand-blasting, in order to improve the surface's mechanical fixation properties. (in situations as metal tanks or similar, must achieve an SP10 according to SSPC norms/NACE 2/2nd quality according to UK norm/DS 2.5 french norm/SA 2 1/5 Sweden norm)
- check the seals and overlaps and where necessary seal with MASTIC PU mastic or TECNOBAND 100 in combination.
- for rapid and efficient cleaning of the surface using a ketone-based solvent.
- apply prior priming using a 100% solids epoxy resin PRIMER EP-1040 or a water-based epoxy resin PRIMER EPw-1070, to improve surface leveling and bonding. Consult the technical specifications of this product.
- application of the TECNOCOAT P-2049 EL pure polyurea membrane. (recommended 1,5 mm)
- application of the polyurethane resin TECNOTOP 2C/S-3000//1C, in consumption and desired thicknesses in the case of no protection against UV rays.

#### Notes:

- Consult in all cases the waiting times, drying time, singular points treatment, conditions of applying all the products through the technical data sheets of each product, the technical guidelines, or consulting our technical department.
- For other types of supports/substrates, for further information on the execution application procedure, for any additional questions, please, consult the technical data sheets (TDS) of these products, or our technical department.



## REPAIR AND OVERLAPS PROCESSES

### REPAIR

In cases where the membrane repair by accidental causes, or assembly procedures not covered installations, shall be as follows:

- cut, removal of the affected area and/or damaged surface
- sanding this area extending about 20–30 cm. around the perimeter, for overlapping security
- cleaning (vacuuming) of waste generated (powder, dust...); if it's possible don't use water, and if used, support humidity value; ketones applicability based solvents for reducing this type of surface cleaning
- apply a thin layer (100-150 g/sqm) of polyurethane resin PRIMER PU-1050, PRIMER EPw-1070
- light spread SILICA SAND over the wet primer applied before
- wait for the total drying
- apply TECNOCOAT P-2049 EL ; compatibility also with: TECNOCOAT CP-2049, TECNOCOAT CP-2049 PLUS, DESMOPOL with DESMOPLUS or DESMOPLUS 700
- apply TECNOTOP S-3000/2C/1C, in consumption and desired thicknesses in the case of no protection against UV rays. This application can be done by short hair roller type equipment "airless" (see the conditions of application in the product datasheet TDS)

### OVERLAPS

In cases has been exceeded recoat time (24~48 hours), so the waiting time between jobs is prolonged, proceed as follows:

- sanding strip longitudinal overlap of about 20–30 cm. wide
- cleaning (vacuuming) of waste generated (powder, dust...)or existing dust; if it's possible, do not use water, and if it's used, check the support humidity value; ketones applicability based solvents for conducting this type of surface cleaning
- apply a thin layer (100-150 g/sqm) of polyurethane resin PRIMER PU-1050, PRIMER EPw-1070
- light spread SILICA SAND over the wet primer applied before
- wait for the total drying
- apply TECNOCOAT P-2049 EL; compatibility also with: TECNOCOAT CP-2049, TECNOCOAT CP-2049 PLUS, DESMOPOL with DESMOPLUS or DESMOPLUS 700
- apply TECNOTOP S-3000/2C/1C, in consumption and desired thicknesses in the case of no protection against UV rays.

## APPLICATION REQUIREMENTS (SPRAY EQUIPMENT)

For the formation, it is necessary to mix the two initial liquid components, isocyanates and amines by our spray equipment TC2049 ([spray-equipment.tecnopolgroup.com](http://spray-equipment.tecnopolgroup.com)) or similar (proper maintenance and cleaning it is recommended). The general parameters for this material will be the following:

- Isocyanate heater temperature:78-80 °C
- Amine heater temperature: 65-70 °C
- Hose temperature:±72°C
- Working pressure: 2.500 - 3.000 psi
- Recommended mixing chamber: GU-07008-1 (*use mechanical purge chamber*)

Anyway, these parameters for adjusting the projection equipment are approximate and may change depending on the weather conditions of the environment at the moment to apply, therefore, it is the responsibility of the applicator values in each case the option to choose.

## HANDLING AND SAFETY



These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery. Always read the MSDS before use and handling the product.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.
- Vapor and atomized liquids are harmful
- Use only in ventilated areas, wear approved respirators when necessary
- Keep out of reach of children
- Do not use near high heat or open flame

Anyway, consult the material and safety data sheet (MSDS) of the product. To obtain an MSDS, please call +34935682111 or send an email to [dpont@tecnopol.es](mailto:dpont@tecnopol.es)

## COMPLEMENTARY PRODUCTS

The TECNOCOAT P-2049 EL system may be complemented with the following products as a means of protection or to improve its physical-mechanical properties depending on its exposure, the desired finish, or the type of substrate.

- PRIMER EP-1010: 100% solids, two-component, fillerized epoxy resin, to fill in depressions in concrete surfaces, one coat application so, rapidly providing a firm and fast drying even base.
- PRIMER EP-1020: 100% solids, two-component, epoxy resin, improving the adhesion, in one coat application so, rapidly providing a firm and fast drying even base.
- PRIMER PU-1050/PUC-1050: these several resins are applied on the substrate beforehand to improve bonding and level the surface and regulate the humidity in the substrate (see permitted levels in their technical specifications).
- PRIMER EP-1040: epoxy resin for its previous application on metallic or ceramic supports, improving adhesion, absorbing resident moisture in the support, and regularizing the planimetry of the support.
- PRIMER EPw-1070: epoxy water-based resin for the application on concrete, asphalt sheets, metal, or ceramic, improving adhesion, absorbing resident moisture in the support.
- PRIMER WET: epoxy resin for the application on concrete or ceramic substrates, improving adhesion, absorbing resident moisture in the substrate.
- TECNOCOAT CP-2049: pure cold polyurea coating for manual application, self-leveling for small applications on TECNOCOAT P-2049 EL, repairs or application in areas of difficult access
- TECNOCOAT CP-2049 PLUS: pure cold polyurea coating for manual application, self-leveling for small applications on TECNOCOAT P-2049 EL, repairs or application in areas of difficult access. It is certified by a European Technical Approval (ETA 20/0253) under EAD 030350-0402 for roofing.
- TECNOTOP 2C: dual-component colored aliphatic polyurethane resin, used to protect walkable and vehicular roofs and floors or ground against UV rays when there is no other protection.
- TECNOTOP 2CP: dual-component colored aliphatic polyurethane resin used to protect against UV rays and chlorinated water when waterproofing swimming pools, lakes, and aquariums.
- TECNOTOP 1C: single component colored aliphatic, used to protect non-walkable roofs or only for maintenance, against UV rays when there is no other protection
- TECNOTOP S-3000: (polyaspartic resin) two-component, aliphatic, colored, cold polyurea coating for protection against UV rays, in situations of decks or floors without additional protection. Excellent for vehicular cover applications, quick-drying, and setting up.
- TECNOPLASTIC: this plastic powder, once mixed with TECNOTOP 2C/2CP/S-3000/1C, forms a rough surface, conforming even to norm ENV 12633:2003 (floors slipperiness), to achieve Class 3 (>45 slip resistance), depending on dosage (consult our technical department).
- TECNOBAND 100: the cold bond deformable band is made up of an upper layer of non-woven textile and a



lower layer of viscoelastic self-adhesive coating, which together allow it to adapt to the shape of the substrate. This band is ideal when dealing with structural joints and overlapping metal materials.

- MASTIC PU: polyurethane mastic for filling joints (use together with TECNOBAND 100 when necessary)

## TECHNICAL DATA OF COMPONENTS

PROPERTIES	COMPONENT A	COMPONENT B*
Density ISO 1675	1,12 ± 0,03 g/cm <sup>3</sup>	1,09 ± 0,03 g/cm <sup>3</sup>
Viscosity (at 12 rpm) ISO 2555	1.200±50 cps	1.000±150 cps
Mix ratio – in weight	100	102
Mix ratio – in volume	100	100

\* Data for component B pigmented in gray. For other colorations or neutral, consult the official COA issued by Tecnopol (Certificate of Analysis for each batch delivered). Results were performed in the laboratory at 23°C and 50% RH, under controllable conditions.

## MEMBRANE PROPERTIES

PROPERTIES	RESULT
Density ISO 1675	±1,15 ±0,03 g/cm <sup>3</sup>
Initial dry time	±13~25 sec
Cured time	±12 hours
Elongation at break ISO 527-3	>600%
Elongation at break at -40 °C ISO 527-3	>350%
Tensile strength ISO 527-3	±13 MPa
Tensile strength at -40 °C ISO 527-3	±23 MPa
Hardness Shore A/D DIN 53.505	>75 / >35
Climatic zone	S (severe)
Constructive element slope	zero slope, ponding water admitted
Environmental and support application temperature range	3°C ~ 40°C
Max. relative humidity	85%
Walkable / Vehicular	±3 hours / ±12 hours
Fire reaction	NPD
Solid content ISO 1768	100%
VOC (volatile organic compounds)	0
Adherence to concrete	>2 MPa

Results were performed in the laboratory at 23°C and 50% RH, under controllable conditions. These values may vary depending on the application, climatology, or substrate conditions.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or



law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

