



TECNOTOP 2C - TWO-COMPONENT, ALIPHATIC POLYURETHANE SOLVENT BASED RESIN SUITABLE AS A FLOORING AND PROTECTION AGAINST UV RAYS

TECNOTOP 2C is a two-component aliphatic, colored, glossy, polyurethane solvent-based, resin for treatment, decoration, flooring and protection of our waterproofing liquid systems (TECNOCOAT y DESMOPOL) in front of UV rays. It has continuous finishing and forms a hard, strong, continuous film, with excellent adhesion and mechanical properties as its excellent resistance to abrasion and stress that make it resistant to weathering, extreme temperature. It is suitable for coating protection for car traffic.



USES

Polyurethane resin to use in the next situations:

- As a continuous surface coating for industrial or commercial resistant flooring use.
- Protection against UV rays on TECNOCOAT and DESMOPOL, waterproofing membranes on flat or sloped roofs, terraces, and balconies, car transit included.
- coating for epoxies systems Tecnofloor T-3020 and Tecnofloor Tw-3040

NOTE: call our technical department about the application to other supports or situations

| | |
|---------------------------|--|
| density | ±1,20 g/cm ³ |
| approx. total consumption | 150~300 g/m ² (depending on final scope) |
| drying time | ±2 hours |
| recoat time | 2~48 hours |
| dilution | DESMOSOLVENT (max. 5-7%), in case of mechanical application |
| application method | by brush, by a short nap acrylic wool roller or "airless" equipment, always thin coats application |



COLORS

| | |
|--|-------------------|
| | Neutral |
| | Grey RAL 7042 |
| | Red tile RAL 8004 |
| | Chart RAL* |

* For special pigmentations and minimum quantities, please see page Sale conditions on the price list



GENERAL FEATURES

- It is a glossy, aliphatic, colored or translucent, solvent-based polyurethane resin
- The translucent version can be colored mixing PIGMENTS PU during the installation (20% on weight)
- The colored version, it's served on any RAL color, except metallic ones (check Sale Conditions on the price list)
- It has an SRI Index according to ASTM E1980-11 (TECNOTOP 2C White color)
- It forms a continuous coating, easy to clean and maintain, and resistant to algae and mold growth.
- Suitable for ponding water, and works under ponding water on a variety of surfaces: concrete, cement, ceramics, TECNOCOAT, or DESMOPOL membranes (for UV rays protection)
- TECNOTOP 2C should be applied in dry conditions avoiding the presence of humidity or water coming from the surface to be coated or the substrate, whether at the time of application or subsequently (pressure from phreatic water level).
- In the event there is humidity in the substrate at the time of application, consult the technical specifications of our primers where their maximum humidity ranges are specified.
- The final product is obtained by mixing 100% of the two components. If only part of the product is used, make sure that this ratio is always maintained to ensure that the final result retains the product's best qualities.
- It can be thinned using DESMOSOLVENT, up to 5% for applications with airless spray equipment.
- Do not apply for swimming pool coatings (see TECNOTOP 2CP)

YIELD

The yield of TECNOTOP 2C varies depending on the layers applied, the type of substrate, or the final use. After mixing both components using an electrical stirrer (low-medium speed), apply thin coats by a short nap acrylic wool roller brush or airless spray equipment; consumption is approximately 150~200 g/m²/layer to get a maximum of 300 g/m² depending on the final use or kind of application. Consult consumptions to our technical department or see the waterproofing liquids systems' Technical Guidelines.

PACKAGING

Metal tins in two different formats:

- LARGE: 17,2 kg + 2,8 kg
- SMALL: 4,3 kg + 0,7 kg (only in neutral and grey color)

SHELF LIFE

Component A expires after 24 months, component B expires after 12 months, at temperatures between 5° C and 35°, provided it is stored in a dry place. Once the tin has been opened, it must be used immediately.

APPLICATION METHOD

In general, you should take the following factors:

- repair the surface (fill in depressions, eliminate unevenness, eliminate any old waterproofing, etc.)
- detail works(perimeter, sinks/drainages, expansion joints, or structural)
- clean up the surface or substrate, removing any dust, dirt, grease, or efflorescence.
- the surface has to be enough compressive strength of adhesion of the membrane. If it were not so, we will proceed to apply our primers resins to achieve this target
- in the case of Tecnotop 2C neutral version, add the proper quantity of PIGMENTS PU(20%) inside the component A and mix until getting a homogenized product, using an electric mixer medium speed; after that, add component B
- in the case of Tecnotop 2C already pigmented, pour component B on component A and stir to getting a



homogenized product

- in case of doubt of all above, apply before in a restricted area and to check

TECNOTOP 2C can be applied to many different surfaces and the procedure will vary depending on its nature or state. Below we set out some of the applications for the most common surfaces; for other surfaces not described, please contact our technical department.

TECNOCOAT/DESMOPOL, waterproofing membranes

- clean up the surface or substrate, removing any dust, dirt, grease, or efflorescence
- apply PRIMER PU-1000/PRIMER EPw-1070, with a yield of approximately 50~70 g/m², if the time of application of membrane(TECNOCOAT or DESMOPOL) is over 24~48 h, and depending on the state of the substrate or the surface's porosity too.
- apply by a short nap acrylic wool roll, thin layers of colored TECNOTOP 2C (total consumption 200 - 300 g/m², depending on the scope)

Cement or concrete surfaces

- any depressions or voids should be repaired using a mix (ratio of $\pm 1:4$) of our epoxy resin PRIMER EP-1020 mixed with silica sand.
- fill joints with MASTIC PU, polyurethane mastic
- the concrete should be completely cured (concrete curing takes 28 days), or, in any case, the maximum level of humidity allowed for the substrate should be verified, depending on the primer used.
- any concrete laitance or release agents should be eliminated and an open-pore surface achieved by grit blasting, milling, or sanding.
- clean up the surface or substrate, removing any dust, dirt, grease, or efflorescence.
- apply PRIMER PU-1050/PRIMER PUc-1050/ PRIMER PU-1000, with a yield of approximately 250 g/m² (two or more thin coats) always depending on the state; or apply PRIMER WET, total consumption around 450 g/m². Consumptions depending on the state of the substrate or the surface's porosity or humidity.
- apply by a short nap acrylic wool roller, thin layers of colored TECNOTOP 2C (total consumption 300 g/m² depending on the scope)

Ceramic surfaces

- continuous sanding of the surface, to avoid the addition of water to the substrate. This action will lead to the opening of the pore of the ceramic flooring, cleaning of adhering efflorescence or dirt, and regularisation of the surface, without the addition of water.
- on ceramic surfaces, there must be no empty joints, elements, or loose pieces. They must be filled with MASTIC PU or with our mortar made with our epoxy resin PRIMER EP-1020 and silica aggregate (ratio $\pm 1:4$), or cementitious materials used to make joints.
- in existing expansion joints: empty old material, clean and fill with MASTIC PU. Complement the joints with TECNOBAND 100 if necessary (in joints greater than 20 mm wide).
- after that, the entire surface must be cleaned and removed from contaminants such as dust or particles from these previous processes by mechanical vacuuming.
- apply PRIMER EP-1040 epoxy resin with a total consumption of 100-150 g/m² or PRIMER EPw-1070 epoxy water-based resin, with a total consumption of around 150-200 g/m² (two or more thin coats) always depending on the state of the substrate or the surface's porosity.
- apply with a short nap acrylic wool roller, thin coats of colored TECNOTOP 2C (total consumption 300 g/m² depending on the scope)

Painted surfaces

- if the existing paint is in good condition, clean the surface with a mixture of water and industrial detergent. Leave to dry.
- remove the existing paint if it does not offer good bonding conditions and eliminate any substrate in poor



- condition as this could hamper TECNOTOP 2C bonding.
- clean up and leave to dry
- apply PRIMER EP-1040 epoxy resin with a total consumption of 100-150 g/m² or PRIMER EPw-1070 epoxy water-based resin, with a total consumption of around 150-200 g/m² (two or more thin coats) always depending on the state of the substrate or the surface's porosity.
- apply by a short nap acrylic wool roller, thin coats of colored TECNOTOP 2C (total consumption 300 g/m² depending on the scope)

APPLICATION FINISHINGS

If so required, TECNOTOP 2C can be applied with a non-slip finish as follows:

multilayer system, adding SILICA SAND

- apply an initial coat of TECNOTOP 2C, by a short nap acrylic wool roller mechanical equipment in the thin coat (consumption of 100-150 g/m²)
- spread with SILICA SAND, over the still wet resin. Consumption up to the final client or user
- wait for the drying
- remove silica sand not adhered using a broom; repair the areas without bonded sand
- apply an initial coat of TECNOTOP 2C, by a short nap acrylic wool roller or mechanical equipment in the thin coat (consumption of 100 g/m²)

TECNOPLASTIC F/C system

- mix our TECNOPLASTIC F/C with the desired mixing ratio, maximum 8-9%, recommended $\pm 7\%$ in the Tecnotop 2C component A package.
- add the Tecnotop 2C component B in the initial mixture, beat with electrical mixing equipment at medium speed
- paving a layer of mixed TECNOTOP 2C, by a short nap acrylic wool roller and made in thin layers (consumption approximately 150-175 g/m²).
- if necessary, apply a second final coat of TECNOTOP 2C without mixing with TECNOPLASTIC F/C. The system is also certified to comply with the ENV 12633:2003, according to its dosage (consult our technical department).

Notes:

- Consult in all cases the waiting times, drying time, singular points treatment, conditions of application of all the products through the technical data sheets of each product, the technical handbook of application of TECNOCOAT, or consult our technical department.
- For other types of supports/substrates, for further information on the execution application procedure, for any additional questions, please, consult the technical data sheets (TDS) of these products, or our technical department.

HANDLING AND SAFETY

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.



Anyway, consult the material and safety data sheet of the product (MSDS) or contact our technical department.

COMPLEMENTARY PRODUCTS

TECNOTOP 2C may be complemented with the following products as a means of protection or to improve its physical-mechanical properties depending on its exposure, the desired finish, or the type of substrate.

- PRIMER EP-1010: 100% solids, two-component, fillerized epoxy resin, to fill in depressions in concrete surfaces, one coat application so, rapidly providing a firm and fast drying even base.
- PRIMER PU-1050/PRIMER EP-1040/PRIMER EPw-1070/PRIMER PUc-1050 / PRIMER PU-1000 /PRIMER EP-1020: these several resins are applied on the substrate beforehand to improve bonding and level the surface, as well as regulating the humidity in the substrate (see permitted levels in their technical specifications). Consumption may vary depending on the type of support, nature, or surface texture. Consult the technical specifications of each product or our technical department.
- TECNOPLASTIC F/C: this plastic powder, once mixed with TECNOTOP 2C forms a rough surface, conforming even to norm ENV 12633:2003 (floors slipperiness), to achieve Class 3 (>45 slip resistance), depending on dosage (consult our technical department).
- TECNOBAND 100: the cold bond deformable band made up of an upper layer of non-woven textile and a lower layer of viscoelastic self-adhesive coating, which together allow it to adapt to the shape of the substrate. This band is ideal when dealing with structural joints and overlapping metal materials.
- MASTIC PU: polyurethane mastic for filling joints (use together with TECNOBAND 100 when necessary).



TECHNICAL FEATURES

| PROPERTIES | VALUES |
|--|--|
| Density ISO 1675 | ±1,20 g/cm ³ |
| Viscosity ISO 2555 | 2.000 - 2.300 cps |
| Density components A/B ISO 1675 | ±1,25 g/cm ³ - ±1,08 g/cm ³ |
| Viscosity components A/B ISO 2555 | 4.000 ±1.000 cps - 275 ±50 cps |
| Solid contents ISO 1768 | ±71% |
| Mixing ratio | 1:0.16 |
| VOC(volatile organic compounds) | 340/230 g/l |
| Pot life | ±1 hour |
| Drying time | ±2 hours |
| Complete cured time | 7 days |
| Repaint time | 2-48 hours |
| Elongation at break (test made on polyurea membrane) ISO 527-3 | ±95% |
| Environmental/support temperature range | 5 °C~ 35 °C |
| Use/service range temperature | -20 °C~80 °C |
| Walkable / Vehicular | ±12 hours / ±24 hours |
| Adherence to concrete | >2 MPa |
| Application method | by a short nap acrylic wool roller or airless equipment, always thin coats |
| Dilution (machine application) | DESMOSOLVENT (max. 5-7%) |

Results performed in the laboratory at 23°C and 50% RH, under controllable conditions. These values may vary depending on the application, climatology, or substrate conditions.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

